

Ultra™ series

Fibre



Fibre concrete is Lafarge's polypropylene micro fibre reinforced ready-mixed concrete.

Where to use:

- Driveways
- Pathways
- Sprayed shotcrete concrete
- External paving
- Precast elements
- Cold-floors
- Any other concrete application where enhanced properties are required
- Floors (Industrial , commercial or domestic)

Advantages:

- Reduces the possibility of spalling of concrete edges
- Reduces labour required
- Simplifies the construction process
- Improved concrete properties
- Improved impact and abrasion resistance
- Turns concrete into a composite material that slows crack formation and reduces plastic shrinkage cracking
- Impact and wear-resistance can also be enhanced
- Reduce the overall bleed and consequential settlement cracking

Minimum Standards for Ultra™ Fibre Concrete:

- **Grade of Concrete:** Greater than 15Mpa
- **Cement Type:** Any combination
- **Aggregate Size:** Available with all standard aggregate sizes
- **Consistence:** S2 and greater (for lower workability please seek guidance from Lafarge's technical team)
- **Fibres:** 3mm, 6mm, 12mm, 19mm

- Drastically reduces the potential for plastic shrinkage cracking to occur by constantly redirecting micro cracks each time a fibre filament is encountered.
- Reduces the permeability of concrete through the reduction in bleed water, which reduces the development of capillary pores associated with bleed water. This reduction of pores also decreases the absorption properties and sustainability.
- Greater impact resistance: Impact damage is common in concrete, particularly at the surface and edges of elements and saw cuts. Micro fibres reduce the spalling of the concrete by providing secondary reinforcing.
- Improved abrasion resistance. As micro fibres control bleed water migration, the possibility of the fine cement and sand particles segregating from the mix is drastically reduced. This promotes an efficient hydration of cement which improves the bonding of the cement matrix and achieves a tougher more durable concrete surface
- Improved freeze thaw resistance. The ability of the concrete to take up water is reduced as a consequence of the lower permeability and absorptivity associated with reduced bleeding. Any water that is taken up and freezes will generate tensile force as it expands. These expansion forces are resisted by the micro fibres in the concrete.

“We aim to deliver an excellent customer experience through service, quality, accountability and value“



General Guide lines

- The standard rules for good concrete practice and placing must be strictly observed with proper curing procedures as required by normal concrete mixes.
- The concrete will behave in a similar way to conventional concrete.
- The concrete will be delivered in a uniform consistency. It is advisable not to add water on site.
- The concrete workability for your chosen application must be agreed at the time of ordering.

Safety Precautions:

- The use of safety goggles, hard hat, ear defenders and gloves is recommended when placing concrete.



Lafarge Aggregates & Concrete Iraq
Mam Street, Al-Adala District, Southern Industrial Zone
Erbil - Iraq
Tel: +964 750 334 5810
+964 750 231 8463

LAFARGE
لافارج